



Rodacciai

STAINLESS STEEL REINFORCING BARS
TECHNICAL DATA SHEET

STAINLESS STEEL REINFORCING BARS



RODINOX® stainless ribbed round is the answer to concrete reinforcement problems when high durability is required in the presence of particular climatic and environmental conditions, such as for example the possibility of contact with chlorides due to proximity to the sea or due to anti-ice salting of the streets.

In these situations, in fact, concrete reinforcement with carbon steel is not sufficient and it is therefore opportune to use stainless steel, whose characteristics are optimally exploited in the construction field as:

- it is suitable for use in seismic areas thanks to high plasticity, a high fatigue limit,

and the absence of fragility;

- it resists to low temperatures without brittleness phenomena;

- it resists to high temperatures, including flame and fires;

- it is suitable for use in the hospitals and in the airport control towers thanks to a very low magnetic permeability so that it does not alter the operation of sensitive electronic equipment.

The use of RODINOX® stainless steel, furthermore, drastically reduces maintenance costs, lengthening the life cycle of the object, with appreciable results even in the first years.

RODINOX® conforms to the well-known **British Standard BS 6744:2023**, widely used in the construction sites all over the world, and to the **Italian Ministry Decree** for buildings. In addition, on request, it may conform also to other national and international standards, so it can be used in various Countries.

RODINOX® GRADES

In order to meet the various needs, RODINOX® is manufactured in the following types

| GRADE | TYPE | REFERENCE STEEL | |
|--------------------|----------------------------|--------------------|--------------------------|
| RODINOX® R1 | austenitic al Cr - Ni | 304 / 304L / 304LN | 1.4301 / 1.4307 / 1.4311 |
| RODINOX® R2 | austenitic al Cr - Ni - Mo | 316L / 316LN | 1.4404 / 1.4406 |
| RODINOX® R3 | austenitic al Cr - Ni - Mo | 316HMo / 316LNMo | 1.4436 / 1.4429 |
| RODINOX® R4 | duplex | 2304 | 1.4362 |
| RODINOX® R5 | duplex | 2205 | 1.4462 |

RODINOX® REFERENCE STANDARDS

It can be produced in accordance with the following standards:

| GRADE | Ministerial Decree 17.01.2018 "Technical Standards for Construction" class B450C | | BS 6744: 2023 | |
|---------------------|--|----------------|-----------------|----------------|
| | Coils 6 - 14 mm | Bars 6 - 26 mm | Coils 6 - 14 mm | Bars 6 - 26 mm |
| RODINOX® R1 | Coils 6 - 14 mm | Bars 6 - 26 mm | Coils 6 - 14 mm | Bars 6 - 26 mm |
| RODINOX® R2 | Coils 6 - 14 mm | Bars 6 - 26 mm | - | - |
| RODINOX® R3 | Coils 6 - 14 mm | Bars 6 - 26 mm | Coils 6 - 14 mm | Bars 6 - 26 mm |
| RODINOX® R4* | Bars 6 - 26 mm | | Coils 6 - 14 mm | Bars 6 - 26 mm |
| RODINOX® R5* | - | | Coils 6 - 14 mm | Bars 6 - 26 mm |

* conforms to BS 6744:2023 standard

THE SIZE RANGE RODINOX®

It is available in rolls in the range from 6 to 14 mm and in bars in the range from 6 to 26 mm



CHEMICAL COMPOSITION

The average chemical composition of RODINOX® is as follows:

| MARK | GRADE | C | Mn | Si | S | P | Cr | Ni | Mo | N | Cu |
|-------------|-------------------|------|-----|-----|--------|---------|------|------|-----|------|------|
| RODINOX® R1 | 1.4301 - 1.4307 | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,045 | 18,5 | 8,1 | - | 0,08 | - |
| | 1.4311 - 1.4301 * | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,045 | 18,5 | 8,1 | - | 0,15 | - |
| RODINOX® R2 | 1.4404 | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,04 | 18,0 | 10,1 | 2,1 | 0,08 | - |
| | 1.4406 | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,04 | 18,0 | 10,1 | 2,1 | 0,15 | - |
| RODINOX® R3 | 1.4436 | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,04 | 17,1 | 11,1 | 2,6 | 0,08 | - |
| | 1.4429 | 0,02 | 1,6 | 0,5 | <0,010 | ≤ 0,04 | 17,1 | 11,1 | 2,6 | 0,15 | - |
| RODINOX® R4 | 1.4362 | 0,02 | 0,8 | 0,5 | <0,010 | ≤ 0,035 | 23,2 | 4,1 | 0,2 | 0,10 | 0,30 |
| RODINOX® R5 | 1.4462 | 0,02 | 0,8 | 0,5 | <0,010 | ≤ 0,035 | 22,8 | 5,2 | 3,1 | 0,20 | - |

* conforms to BS 6744:2023 standard

MECHANICAL PROPERTY

According to BS 6744:2023 Rp02=500MPAmin / Rm/Rp02=1,08 min / A5=14%min / AGT=5%min

According to Ministerial Decree 14/01/2008 Rm=540 MPa min - Rp02=450/562 MPa - f7/Rp02=1,15/1,35 - AGT%=7,5% min

THE WEIGHT OF RODINOX®

Mass per linear meter as a function of the type of steel (units kg/m)

| GRADE | Ø nom. mm | 6 | 8 | 10 | 12 | 14 | 16 | 18 | 20 | 22 | 24 | 25 | 26 |
|-------------|-------------------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | section mm ² | 28,3 | 50,3 | 78,5 | 113,1 | 153,9 | 201,1 | 254,5 | 314,2 | 380,1 | 452,4 | 490,9 | 530,9 |
| RODINOX® R1 | | 0,224 | 0,397 | 0,620 | 0,893 | 1,216 | 1,589 | 2,011 | 2,482 | 3,574 | 3,003 | 3,878 | 4,194 |
| RODINOX® R2 | | 0,226 | 0,402 | 0,628 | 0,905 | 1,231 | 1,609 | 2,036 | 2,514 | 3,619 | 3,041 | 3,927 | 4,247 |
| RODINOX® R3 | | 0,226 | 0,402 | 0,628 | 0,905 | 1,231 | 1,609 | 2,036 | 2,514 | 3,619 | 3,041 | 3,927 | 4,247 |
| RODINOX® R4 | | 0,221 | 0,392 | 0,612 | 0,882 | 1,200 | 1,569 | 1,985 | 2,451 | 3,529 | 2,965 | 3,829 | 4,141 |
| RODINOX® R5 | | 0,221 | 0,392 | 0,612 | 0,882 | 1,200 | 1,569 | 1,985 | 2,451 | 3,529 | 2,965 | 3,829 | 4,141 |

Tolerance on mass per meter Up to 6mm = + 9% - 7 to 12 mm = + 6% - Over 12mm = + 4.5%



www.rodacciai.com
www.rodinox.net



Rodacciai S.p.a. - Headquarter
Bosisio Parini (LC) Via Giuseppe Roda 1, 23842
Tel. +39 031878111 - info@rodacciai.com
www.rodasteel.ch